



Digital Materials Data Sheet

RIGID OPAQUE MATERIALS

PRIMARY MATERIAL: VEROWHITEPLUS™ RGD835 SECONDARY MATERIAL: VEROBLACKPLUS™ RGD875			
PROPERTY	ASTM	UNITS	RGD8310-DM, RGD8320-DM, RGD8330-DM
Tensile strength	D-638-03	MPa	50-65
Elongation at break	D-638-05	%	10-25
Modulus of elasticity	D-638-04	MPa	2000-3000
Flexural strength	D-790-03	MPa	75-110
Flexural modulus	D-790-04	MPa	2200-3200
HDT, °C @ 0.45MPa	D-648-06	°C	45-50
Izod notched impact	D-256-06	J/m	20-30

PRIMARY MATERIAL: VEROWHITEPLUS RGD835 SECONDARY MATERIAL: TANGOBLOCKPLUS™ FLX980 / TANGOPLUS™ FLX930				
PROPERTY	ASTM	UNITS	RGD8505-DM RGD8510-DM RGD8515-DM RGD8520-DM	RGD8525-DM RGD8425-DM (ONLY OBJET TANGOPLUS FLX930)
Tensile strength	D-638-03	MPa	40-60	35-45
Elongation at break	D-638-05	%	15-25	20-30
Modulus of elasticity	D-638-04	MPa	1700-2300	1400-2000
Flexural strength	D-790-03	MPa	55-75	45-60
Flexural modulus	D-790-04	MPa	1500-2500	1400-1800
HDT, °C @ 0.45MPa	D-648-06	°C	40-45	40-43
Izod notched impact	D-256-06	J/m	22-35	22-35
Shore hardness (D)	D2240-05	Scale D	81.1-85.5	79.5-83.5

PRIMARY MATERIAL: HIGH TEMPERATURE RGD525 SECONDARY MATERIAL: TANGOBLOCKPLUS FLX980				
PROPERTY	ASTM	UNITS	RGD5205-DM RGD5210-DM RGD5215-DM RGD5220-DM RGD5225-DM	RGD5250-DM*
Tensile strength	D-638-03	MPa	43-55	50-56
Elongation at break	D-638-05	%	9-15	18-27
Modulus of elasticity	D-638-04	MPa	1600-2700	1700-2400
Flexural strength	D-790-03	MPa	50-100	47-70
Flexural modulus	D-790-04	MPa	1700-2700	1400-2000
HDT, °C @ 0.45MPa	D-648-06	°C	46-60	50-56
Izod notched impact	D-256-06	J/m	16-19	16-26

PRIMARY MATERIAL: VEROBLOCK™ RGD840 SECONDARY MATERIAL: VEROBLACKPLUS RGD875			
PROPERTY	ASTM	UNITS	RGD8210-DM
Tensile strength	D-638-03	MPa	50-60
Elongation at break	D-638-05	%	15-25
Modulus of elasticity	D-638-04	MPa	2000-3000
Flexural strength	D-790-03	MPa	60-70
Flexural modulus	D-790-04	MPa	1900-2500
HDT, °C @ 0.45MPa	D-648-06	°C	45-50
Izod notched impact	D-256-06	J/m	20-30

PRIMARY MATERIAL: VERO BLACKPLUS RGD875 SECONDARY MATERIAL: TANGOBLOCKPLUS FLX980 / TANGOPLUS FLX930			
PROPERTY	ASTM	UNITS	RGD8555-DM RGD8455-DM
Tensile strength	D-638-03	MPa	35-45
Elongation at break	D-638-05	%	20-30
Modulus of elasticity	D-638-04	MPa	1400-2000
Flexural strength	D-790-03	MPa	45-60
Flexural modulus	D-790-04	MPa	1400-1800
HDT, °C @ 0.45MPa	D-648-06	°C	40-43
Izod notched impact	D-256-06	J/m	25-35
Shore hardness (D)	D2240-05	Scale D	79.5-83.5

PRIMARY MATERIAL: HIGH TEMPERATURE RGD525 SECONDARY MATERIAL: TANGOPLUS FLX930			
PROPERTY	ASTM	UNITS	RGD5150-DM
Tensile strength	D-638-03	MPa	45-60
Elongation at break	D-638-05	%	18-27
Modulus of elasticity	D-638-04	MPa	1700-2400
Flexural strength	D-790-03	MPa	47-70
Flexural modulus	D-790-04	MPa	1400-2000
HDT, °C @ 0.45MPa	D-648-06	°C	50-56
Izod notched impact	D-256-06	J/m	16-26

* Vero™-like DM with higher temperature resistance
Find material properties for color materials on the Color Digital Materials Data Sheet.

RIGID OPAQUE MATERIALS

PRIMARY MATERIAL: VEROWHITEPLUS RGD835
SECONDARY MATERIAL: TANGOBLACK™ FLX973

PROPERTY	ASTM	UNITS	RGD8110 - DM	RGD8120 - DM	RGD8130 - DM
Tensile strength	D-638-03	MPa	45-65	46-65	27-33
Elongation at break	D-638-05	%	10-30	10-30	25-35
Modulus of elasticity	D-638-04	MPa	2000-3000	2000-3000	1500-2100
Flexural strength	D-790-03	MPa	70-100	70-100	40-50
Flexural modulus	D-790-04	MPa	2000-3000	2000-3000	1400-1800
HDT, oC @ 0.45MPa	D-648-06	°C	43-50	43-50	40-45
Izod notched impact	D-256-06	J/m	20-35	20-35	30-40

TRANSPARENT MATERIALS

PRIMARY MATERIAL: RGD720
SECONDARY MATERIAL: VEROBLOCKPLUS RGD875

PROPERTY	ASTM	UNITS	RGD7513-DM (DOTS) RGD7523-DM (GRID)
Tensile strength	D-638-03	MPa	50-65
Elongation at break	D-638-05	%	15-25
Modulus of elasticity	D-638-04	MPa	2000-3000
Flexural strength	D-790-03	MPa	80-110
Flexural modulus	D-790-04	MPa	2700-3300
HDT, oC @ 0.45MPa	D-648-06	°C	45-50
Izod notched impact	D-256-06	J/m	20-30

PRIMARY MATERIAL: RGD720
SECONDARY MATERIAL: TANGOBLACK FLX973

PROPERTY	ASTM	UNITS	RGD7210-DM	RGD7220-DM	RGD7230-DM
Tensile strength	D-638-03	MPa	50-55	50-55	45-50
Elongation at break	D-638-05	%	15-25	15-25	15-25
Modulus of elasticity	D-638-04	MPa	2200-2500	2000-2300	1700-2000
Flexural strength	D-790-03	MPa	80-90	75-85	70-80
Flexural modulus	D-790-04	MPa	2300-2700	2200-2600	2100-2400
HDT, oC @ 0.45MPa	D-648-06	°C	45-50	45-50	45-50
Izod notched impact	D-256-06	J/m	20-30	20-30	20-30

PRIMARY MATERIAL: VEROCLEAR™ RGD810
SECONDARY MATERIAL: TANGOPLUS FLX930 /
TANGOBLACKPLUS FLX980

PROPERTY	ASTM	UNITS	RGD8705-DM RGD8710-DM RGD8715-DM RGD8720-DM	RGD8625-DM RGD8725-DM
Tensile strength	D-638-03	MPa	40-60	35-45
Elongation at break	D-638-05	%	15-25	20-30
Modulus of elasticity	D-638-04	MPa	1,700-2,300	1,400-2,000
Flexural strength	D-790-03	MPa	55-75	45-60
Flexural modulus	D-790-04	MPa	1,500-2,500	1,400-1,800
HDT, oC @ 0.45MPa	D-648-06	°C	40-45	40-43
Izod notched impact	D-256-06	J/m	22-35	25-35
Shore hardness (D)	D2240-05	Scale D	81.1-85.5	79.5-83.5

SIMULATED POLYPROPYLENE MATERIALS

PRIMARY MATERIAL: DURUSWHITE™ RGD430
SECONDARY MATERIAL: VEROWHITEPLUS RGD835, VEROBLOCKPLUS RGD875 OR RGD720

PROPERTY	ASTM	UNITS	RGD4310-DM RGD4410-DM RGD4510-DM RGD4710-DM
Tensile strength	D-638-03	MPa	30-40
Elongation at break	D-638-05	%	40-50
Modulus of elasticity	D-638-04	MPa	1200-1600
Flexural strength	D-790-03	MPa	40-50
Flexural modulus	D-790-04	MPa	1300-1700
HDT, oC @ 0.45MPa	D-648-06	°C	40-45
Izod notched impact	D-256-06	J/m	35-45

PRIMARY MATERIAL: VEROWHITEPLUS RGD835
SECONDARY MATERIAL: TANGOPLUS FLX930 / TANGOBLACKPLUS FLX980

PROPERTY	ASTM	UNITS	RGD8430-DM RGD8530-DM
Tensile strength	D-638-03	MPa	29-38
Elongation at break	D-638-05	%	25-35
Modulus of elasticity	D-638-04	MPa	1100-1700
Flexural strength	D-790-03	MPa	35-45
Flexural modulus	D-790-04	MPa	1200-1500
HDT, °C @ 0.45MPa	D-648-06	°C	38-41
Izod notched impact	D-256-06	J/m	21-40
Shore hardness (D)	D2240-05	Scale D	76.1-81.7

SIMULATED POLYPROPYLENE MATERIALS

PRIMARY MATERIAL: VEROBLOCKPLUS RGD875 SECONDARY MATERIAL: TANGOPLUS FLX930 / TANGOBLOCKPLUS FLX980			
PROPERTY	ASTM	UNITS	RGD8460-DM RGD8560-DM
Tensile strength	D-638-03	MPa	29-38
Elongation at break	D-638-05	%	25-35
Modulus of elasticity	D-638-04	MPa	1100-1700
Flexural strength	D-790-03	MPa	35-45
Flexural modulus	D-790-04	MPa	1200-1500
HDT, °C @ 0.45MPa	D-648-06	°C	38-41
Izod notched impact	D-256-06	J/m	21-40
Shore hardness (D)	D2240-05	Scale D	76.1-81.7

PRIMARY MATERIAL: VEROCLEAR RGD810 SECONDARY MATERIAL: TANGOPLUS FLX930 / TANGOBLOCKPLUS FLX980			
PROPERTY	ASTM	UNITS	RGD8630-DM RGD8730-DM
Tensile strength	D-638-03	MPa	29-38
Elongation at break	D-638-05	%	25-35
Modulus of elasticity	D-638-04	MPa	1100-1700
Flexural strength	D-790-03	MPa	35-45
Flexural modulus	D-790-04	MPa	1200-1500
HDT, °C @ 0.45MPa	D-648-06	°C	38-41
Izod notched impact	D-256-06	J/m	21-40
Shore hardness (D)	D2240-05	Scale D	76.1-81.7

PRIMARY MATERIAL: RIGUR™ SECONDARY MATERIAL: TANGOBLOCKPLUS FLX980			
PROPERTY	ASTM	UNITS	RGD4805-DM RGD4810-DM RGD4815-DM RGD4820-DM
Tensile strength	D-638-03	MPa	25-45
Elongation at break	D-638-05	%	35-45
Modulus of elasticity	D-638-04	MPa	1200-1800
Flexural strength	D-790-03	MPa	30-40
Flexural modulus	D-790-04	MPa	1000-1400
HDT, °C @ 0.45MPa	D-648-06	°C	43-48
Izod notched impact	D-256-06	J/m	50-70
Shore hardness (D)	D2240-05	Scale D	81.1-85.5

PRIMARY MATERIAL: RIGUR SECONDARY MATERIAL: TANGOPLUS FLX930 / TANGOBLOCKPLUS FLX980			
PROPERTY	ASTM	UNITS	RGD4825-DM RGD4830-DM RGD4625-DM RGD4630-DM
Tensile strength	D-638-03	MPa	25-35
Elongation at break	D-638-05	%	35-45
Modulus of elasticity	D-638-04	MPa	900-1500
Flexural strength	D-790-03	MPa	20-35
Flexural modulus	D-790-04	MPa	800-1200
HDT, °C @ 0.45MPa	D-648-06	°C	43-46
Izod notched impact	D-256-06	J/m	50-70
Shore hardness (D)	D2240-05	Scale D	79.5-83.5

RUBBER-LIKE MATERIALS

PRIMARY MATERIAL: TANGOBLOCKPLUS FLX980 / TANGOPLUS FLX930 SECONDARY MATERIAL: VEROWHITEPLUS RGD835								
PROPERTY	ASTM	UNITS	FLX9840-DM FLX9740-DM	FLX9850-DM FLX9750-DM	FLX9860-DM FLX9760-DM	FLX9870-DM FLX9770-DM	FLX9885-DM FLX9785-DM	FLX9895-DM FLX9795-DM
Tensile strength	D-412	MPa	1.3-1.8	1.9-3.0	2.5-4.0	3.5-5.0	5.0-7.0	8.5-10.0
Elongation at break	D-412	%	110-130	95-110	75-85	65-80	55-65	35-45
Shore hardness (A)	D-2240	Scale A	35-40	45-50	57-63	68-72	80-85	92-95
Tensile tear resistance	D-624	Kg/cm	5.5-7.5	7.5-9.5	11-13	15.5-17.5	23-25	41-44

PRIMARY MATERIAL: TANGOBLOCKPLUS FLX980 / TANGOPLUS FLX930 SECONDARY MATERIAL: VEROCLEAR RGD810								
PROPERTY	ASTM	UNITS	FLX9040-DM FLX9940-DM	FLX9050-DM FLX9950-DM	FLX9060-DM FLX9960-DM	FLX9070-DM FLX9970-DM	FLX9085-DM FLX9985-DM	FLX9095-DM FLX9995-DM
Tensile strength	D-412	MPa	1.3-1.8	1.9-3.0	2.5-4.0	3.5-5.0	5.0-7.0	8.5-10.0
Elongation at break	D-412	%	110-130	95-110	75-85	65-80	55-65	35-45
Shore hardness (A)	D-2240	Scale A	35-40	45-50	57-63	68-72	80-85	92-95
Tensile tear resistance	D-624	Kg/cm	5.5-7.5	7.5-9.5	11-13	15.5-17.5	23-25	41-44

RUBBER-LIKE MATERIALS (CONT.)

PRIMARY MATERIAL: TANGOGRAY™ FLX950 SECONDARY MATERIAL: VEROBLACKPLUS RGD875			
PROPERTY	ASTM	UNITS	FLX9610-DM
Tensile strength	D-412	MPa	9-13
Elongation at break	D-412	%	45-55
Shore hardness (A)	D-2240	Scale A	75-85
Tensile tear resistance	D-624	Kg/cm	45-50

PRIMARY MATERIAL: TANGOPLUS FLX930 / TANGOBLOCKPLUS FLX980 SECONDARY MATERIAL: HIGH TEMPERATURE RGD525								
PROPERTY	ASTM	UNITS	FLX9540-DM FLX9640-DM	FLX9550-DM FLX9650-DM	FLX9560-DM FLX9660-DM	FLX9570-DM FLX9670-DM	FLX9585-DM FLX9685-DM	FLX9595-DM FLX9695-DM
Tensile strength	D-412	MPa	1.3-1.8	2.0-2.8	2.8-4.0	3.8-4.9	6.0-7.3	9.0-12
Elongation at break	D-412	%	100-130	80-100	60-80	50-70	35-50	27-40
Shore hardness (A)	D-2240	Scale A	39-41	52-55	60-67	70-78	85-87	95-96
Tensile tear resistance	D-624	Kg/cm	5.0-7.0	8.0-10.0	10.5-12.5	13-15	22.5-24.5	45-47

PRIMARY MATERIAL: TANGOBLOCK FLX973 SECONDARY MATERIAL: VEROWHITEPLUS RGD835(I), VEROBLUE RGD840(III), VEROBLACKPLUS RGD875(IIII), RGD720(II)					
PROPERTY	ASTM	UNITS	FLX9110-DM(I) FLX9410-DM (II) FLX9210-DM (III) FLX9310-DM (IIII)	FLX9120-DM (I) FLX9420-DM (II) FLX9220-DM (III) FLX9320-DM (IIII)	FLX9130-DM (I) FLX9430-DM (II) FLX9230-DM (III) FLX9330-DM (IIII)
Tensile strength	D-412	MPa	2-4.	3-5	7-11
Elongation at break	D-412	%	45-55	35-45	35-45
Shore hardness (A)	D-2240	Scale A	75-85	80-90	90-100
Tensile tear resistance	D-624	Kg/cm	7-9	13-17	45-50

PRIMARY MATERIAL: TANGOGRAY FLX950 SECONDARY MATERIAL: TANGOBLOCK FLX973			
PROPERTY	ASTM	UNITS	FLX9510-DM
Tensile strength	D-412	MPa	1-3
Elongation at break	D-412	%	35-45
Shore hardness (A)	D-2240	Scale A	60-70
Tensile tear resistance	D-624	Kg/cm	5.0-7.0

PRIMARY MATERIAL: TANGOBLOCKPLUS FLX980 / TANGOPLUS FLX930 SECONDARY MATERIAL: VEROBLACKPLUS RGD875								
PROPERTY	ASTM	UNITS	FLX2140-DM FLX2040-DM	FLX2150-DM FLX2050-DM	FLX2160-DM FLX2060-DM	FLX2170-DM FLX2070-DM	FLX2185-DM FLX2085-DM	FLX2195-DM FLX2095-DM
Tensile strength	D-412	MPa	1.3-1.8	1.9-3.0	2.5-4.0	3.5-5	5.5-7.0	8.5-10
Elongation at break	D-412	%	110-130	95-110	75-85	65-80	55-65	35-45
Shore hardness (A)	D-2240	Scale A	35-40	45-50	57-63	68-72	80-85	92-95
Tensile tear resistance	D-624	Kg/cm	5.5-7.5	7.5-9.5	11.0-13.0	15.5-17.5	23-25	41-44

PRIMARY MATERIAL: TANGOBLOCKPLUS FLX930 / TANGOPLUS FLX980 SECONDARY MATERIAL: DIGITAL ABS PLUS™ IVORY								
PROPERTY	ASTM	UNITS	FLX95540-DM FLX95040-DM	FLX95550-DM FLX95050-DM	FLX95560-DM FLX95060-DM	FLX95570-DM FLX95070-DM	FLX95585-DM FLX95085-DM	FLX2195-DM FLX2095-DM
Tensile strength	D-412	MPa	2.3-2.5	3.2-3.5	3.8-4.3	4.7-5.0	7.0-7.7	9.8-10.6
Elongation at break	D-412	%	145-155	125-135	95-110	80-90	50-65	40-50
Shore hardness (A)	D-2240	Scale A	35-45	45-55	55-65	65-75	80-90	90-100
Tensile tear resistance	D-624	Kg/cm	5.5-6.5	8.5-10.5	10.0-12.0	13-15	22-26	42-52

RUBBER-LIKE MATERIALS (CONT.)

PRIMARY MATERIAL: AGILUS30 (FLX2040) / AGILUS30 BLACK (FLX9840) SECONDARY MATERIAL: VERO								
PROPERTY	ASTM	UNIT	FLX9740 FLX9840	FLX9750 FLX9850	FLX9760 FLX9860	FLX9770 FLX9870	FLX9785 FLX9885	FLX9795 FLX9895
Tensile strength	D-412	MPa	3-4	3-4	3.5-4.5	4-6	6-10	10-14
Elongation at break	D-412	%	190-210	170-210	150-170	120-140	70-90	50-70
Shore hardness	D-2240	Scale A	40-50	50-55	55-60	60-70	80-85	85-90
Tensile tear resistance	D-624	Kg/cm	6.0-8.0	7.0-9.0	7.0-10.0	12.0-14.0	22.0-26.0	26.0-30.0

PRIMARY MATERIAL: AGILUS30 (FLX2040) / AGILUS30 BLACK (FLX9840) SECONDARY MATERIAL: DIGITAL ABS PLUS IVORY								
PROPERTY	ASTM	UNIT	FLX95040 FLX95540	FLX95050 FLX95550	FLX95060 FLX95560	FLX95070 FLX95570	FLX95085 FLX95585	FLX95095 FLX95595
Tensile strength	D-412	MPa	2.5-3	2.5-3	3.5-4	4.5-6	6-8	9-11
Elongation at break	D-412	%	180-200	160-180	120-140	90-100	70-80	40-60
Shore hardness	D-2240	Scale A	40-50	45-55	50-60	65-70	80-85	85-90
Tensile tear resistance	D-624	Kg/cm	5.0-7.0	6.0-8.0	7.0-9.0	12.0-15.0	15-19	25-29

PRIMARY MATERIAL: AGILUS30 (FLX2040) / AGILUS30 BLACK (FLX9840) SECONDARY MATERIAL: RIGUR								
PROPERTY	ASTM	UNIT	FLX4640 FLX4840	FLX4650 FLX4850	FLX4660 FLX4860	FLX4670 FLX4870	FLX4685 FLX4885	FLX4695 FLX4895
Tensile strength	D-412	MPa	2.5-3	2.5-3	3-4	3.5-5	5.5-8.5	9-13
Elongation at break	D-412	%	190-210	170-190	150-170	120-140	80-100	50-80
Shore hardness	D-2240	Scale A	40-50	50-60	55-60	65-75	85-90	85-95
Tensile tear resistance	D-624	Kg/cm	4.0-6.0	5.0-9.0	6.0-10.0	8.0-12.0	16-20	25.0-29.0

PRIMARY MATERIAL: TANGOPLUS FLX930 / TANGOBLOCKPLUS FLX980 SECONDARY MATERIAL: RIGUR								
PROPERTY	ASTM	UNIT	FLX4640-DM FLX4840-DM	FLX4650-DM FLX4850-DM	FLX4660-DM FLX4860-DM	FLX4670-DM FLX4870-DM	FLX4685-DM FLX4885-DM	FLX4695-DM FLX4895-DM
Tensile strength	D-412	MPa	1.3-1.8	1.9-3.0	2.5-4.0	3.5-5.0	5.0-7.0	8.5-10.0
Elongation at break	D-412	%	110-130	95-110	75-85	65-80	55-65	35-45
Shore hardness (A)	D-2240	Scale A	35-40	45-50	57-63	68-72	80-85	92-95
Tensile tear resistance	D-624	Kg/cm	5.5-7.5	7.5-9.5	11-13	15.5-17.5	23-25	41-44

stratasys

The data included in this brochure is for your information only and should not be considered specific advice. Each customer is responsible for the design and functionality of their parts. The sale and provision of the products described in this brochure are subject to terms and conditions outlined in Stratasys selling policies, contracts between the parties or Stratasys Terms and Conditions of Sale. This brochure is not intended to add to any such contract or terms.

© 2015, 2017 Stratasys Ltd. All rights reserved. Connex, Digital ABS Plus, Durus, DurusWhite, Rigur, Tango, TangoBlack, TangoBlackPlus, TangoGray, TangoPlus, Vero, VeroBlackPlus, VeroBlue, VeroClear, VeroWhitePlus, "For a 3D World", Stratasys, and Stratasys nautilus logo are trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. MSS_PJ_DigitalMaterialsDataSheet_A4_0617a